

# 8800 Thermal Values

IG Code	IG Makeup	IG Color	U-Factor	SHGC	VT
I6	1" OA (3/16 – 5/8 – 3/16)	Clear	0.45	0.46	0.49
"	"	Bronze	0.45	0.35	0.32
"	"	Light Gray	0.45	0.35	0.32
"	"	Low E 270	0.32	0.23	0.41
"	"	Low E 240	0.32	0.16	0.24
"	"	Low E 366	0.32	0.17	0.39
L21	1" OA (3/16 – 3/8 – 7/16LAMI[3/16-.105 PVB-3/16])	Clear	0.50	0.43	0.48
"	"	Bronze	0.50	0.33	0.31
"	"	Light Gray	0.50	0.30	0.27
"	"	Low E 270	0.41	0.23	0.41
"	"	Low E 240	0.41	0.16	0.23
"	"	Low E 366	0.40	0.18	0.38
L5	1" OA (3/16 – 3/8 – 7/16LAMI[3/16-.090 SGP-3/16])	Clear	0.49	0.43	0.47
"	"	Bronze	0.49	0.33	0.31
"	"	Light Gray	0.49	0.30	0.27
"	"	Low E 270	0.39	0.23	0.40
"	"	Low E 240	0.39	0.16	0.23
"	"	Low E 366	0.39	0.18	0.37